

AVIENT SPECIALTY INKS

PRODUCT INFORMATION BULLETIN



AVIENT SPECIALTY INKS - REDUCERS

Avient™ Specialty Inks offers a range of reducers to lower the viscosity of plastisol inks. These reducers are used as additives to modify the flow and printing characteristics of plastisol inks.

HIGHLIGHTS

- ▶ K2910 VISCOSITY BUSTER
K2912 VISCOSITY BUSTER LC
K2915 CURABLE REDUCER
- ▶ Designed to reduce viscosity in plastisol inks

PRINTING TIPS

- ▶ Stir inks thoroughly when adding reducer
- ▶ 2915 CURABLE REDUCER is an efficient reducer and an addition of 5% by weight will lower the viscosity of most plastisol inks by 25%. Adding curable reducer at recommended amounts will not alter the cure temperature of the plastisol ink. Additions greater than 10% may reduce opacity, bleed and affect cure temperatures
- ▶ 2910 VISCOSITY BUSTER is a concentrated reducer and will stabilize and improve the flow properties of plastisol finished inks. Viscosity buster is concentrated and very efficient in reducing viscosity at small amounts. Start at 0.5% by weight and increase by 0.5% until desired viscosity is reached. Do not use more than 3% by weight
- ▶ 2912 VISCOSITY BUSTER LC is a new technology and sustainable alternative to the 2910 Viscosity Buster. 2912 VISCOSITY BUSTER LC is a concentrated reducer and used to stabilize and improve the flow properties of plastisol finished inks. Viscosity buster is concentrated and very efficient in reducing viscosity at small amounts. Start at 0.5% by weight and increase by 0.5% until desired viscosity is reached. Do not use more than 3% by weight
- ▶ 2910 Viscosity Buster and 2912 Viscosity Buster LC are best used with high viscous plastisol such as whites and blockers when reduction is needed. Please see specific PIBs
- ▶ When using these reducers within the recommended percentages, follow the cure temperature requirements as stated on the relevant plastisol ink PIB. Using these reducers will not lower the cure temperatures
- ▶ With all reducers, any dramatic changes in viscosity may result in altered printing characteristics
- ▶ Store 2912 Viscosity Buster LC at room temperature or above. Avoid storing this product in cold areas or on cold floors. Temperatures below 32°F (0°C) may cause the product to separate

COMPLIANCE

- ▶ Non-phthalate
- ▶ For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications

RECOMMENDED PARAMETERS



Fabric Types

see relevant PIB




Mesh

Count: see relevant PIB
Tension: see relevant PIB



Squeegee

Durometer: see relevant PIB
Profile: see relevant PIB
Stroke: see relevant PIB
Angle: see relevant PIB



Stencil

see relevant PIB
Off Contact: see relevant PIB
Emulsion Over Mesh: see relevant PIB



Flash & Cure

Flash: see relevant PIB
Cure: see relevant PIB



Pigment Loading

N/A



Additives

N/A



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Dispose unused ink responsibly



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR



AVIENT
SPECIALTY
INKS

V1.00 (Modified: 05/10/2021)

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.