



## **MagnaPrint® Crosslinker 100**

MagnaPrint® Crosslinker 100 can be used to considerably reduce the time of curing pigment prints. It is compatible with most MagnaPrint® printing systems.

MagnaPrint® Crosslinker 100 is particularly useful where dryers have insufficient dwell time.

### **Application**

MagnaPrint® Crosslinker 100 can be used at varying concentrations, depending on the product into which it is to be added, but as a general rule do not exceed 20g/kg. Trials should be carried under specific printing conditions to arrive at the correct addition level.

Once added to a print paste, MagnaPrint® Crosslinker 100 will remain active for a maximum of 8 hours. The print paste stability is not adversely affected and the system can be re-activated by a further addition of MagnaPrint® Crosslinker 100.

Minimum curing recommendation - 1 minute at 165°C (330°F)

### **SPECIFICATION**



#### **CURE TEMPERATURE**

1 minute at 165°C - 170°C  
(330 - 340°F)



#### **STORAGE**

In cool place properly closed:  
>5°C (40°F) <25°C (77°F)



#### **HEALTH & SAFETY**

MSDS available upon request



#### **CLEAN UP**

Wash off screen using water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.



**MagnaColours® Limited**  
Upper Cliffe Road,  
Dodworth Business Park,  
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751  
F: 00 44 (0) 1226 731752  
E: [info@magnacolours.com](mailto:info@magnacolours.com)  
[www.magnacolours.com](http://www.magnacolours.com)

Company registered in  
England No. 01378495,  
VAT No. GB 997 3172 70