



## MagnaPrint® Ecofix XL

### Fastness improver for high pigment loadings

MagnaPrint® Ecofix XL is a crosslinking agent, specifically designed to improve wash and rub-fastness. MagnaPrint® Ecofix XL is compatible with all MagnaPrint® bases.

### Application

Add up to 5% MagnaPrint® Ecofix XL, mix well and cure at 140°C (284°F) for 2 mins or 165°C (330°F) for 1.5 minutes

### SPECIFICATION



#### CURE TEMPERATURE

2mins at 140°C (284°F) or  
1½ mins at 165°C (330°F)



#### STORAGE

In cool place properly closed:  
>5°C (40°F) <25°C (77°F)



#### HEALTH & SAFETY

MSDS available upon  
request



#### CLEAN UP

Wash off screen using water  
and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.



**MagnaColours® Limited**  
Upper Cliffe Road,  
Dodworth Business Park,  
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751  
F: 00 44 (0) 1226 731752  
E: [info@magnacolours.com](mailto:info@magnacolours.com)  
[www.magnacolours.com](http://www.magnacolours.com)

Company registered in  
England No. 01378495,  
VAT No. GB 997 3172 70