



## **MagnaPrint® Emboss**

### **Ready to use printing paste for embossed effects**

MagnaPrint® Emboss is a ready to use water-based print paste for achieving an embossed surface to polyester fabrics. The ink is designed to be washed off following use, leaving a raised effect to desired areas of the fabric.

### **Application**

MagnaPrint® Emboss can be printed directly on fabric. Stronger effects can be achieved by using several printing strokes.

Printing is best undertaken using 32 - 43T (80 - 110) mesh screens with rectangular squeegees.

After printing, the fabric should be cured for a minimum of 2 ½ minutes at 165 - 170°C (330 - 340°F). Ideally thoroughly wash the material as soon as possible following curing to remove the ink for the strongest effects.

### **SPECIFICATION**



**FABRIC TYPES**  
Polyester



**MESH**  
32 - 43T (80 - 110)



**SQUEEGEE**  
Medium 65° Shore  
Rectangular



**STENCIL**  
Water resistant emulsion



**CURE TEMPERATURE**  
2 ½ minutes at 170°C  
(340°F)



**STORAGE**  
In cool place properly closed:  
>5°C (40°F) <25°C (77°F)



**HEALTH & SAFETY**  
MSDS available upon request



**CLEAN UP**  
Wash off screen using water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.



**MagnaColours® Limited**  
Upper Cliffe Road,  
Dodworth Business Park,  
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751  
F: 00 44 (0) 1226 731752  
E: info@magnacolours.com  
www.magnacolours.com

Company registered in  
England No. 01378495,  
VAT No. CB 997 3172 70