



## **MagnaPrint® Pearl Flex Neutral**

## Ready to print pearlescent stretchy pastes

MagnaPrint® Pearl Flex Neutral is a ready to use stretchy / flexible print paste containing speciality pigments to obtain a "metallic-like" effect.

MagnaPrint® Pearl Flex Neutral has excellent elasticity properties and can be printed directly onto the fabric to achieve fantastic stretch and durability without the need for an under base

MagnaPrint® Pearl Flex Neutral can be pigmented with the addition of up to 6% Eco Pigments to give desired shade.

## **Application**

MagnaPrint® Pearl Flex Neutral should be printed through a 32-61 (86 -156) mesh screens with rectangular profile squeegees.

As the particle size is 10-60 micron this should be considered when selecting screen mesh.

When printing as part of a multicoloured design print the MagnaPrint® Pearl Flex Neutral as the last screen to avoid pick up.

After printing the garment/panel should be cured, ideally for 2 -  $2^{1/2}$  minutes at 165°C (330°F).

## **SPECIFICATION**



FABRIC TYPES Cotton / Poly Cotton blends



**MESH** 32 - 61T (86 - 156)



**SQUEEGEE** Medium 65° Shore Rectangular



**STENCIL**Water resistant emulsion



CURE TEMPERATURE 2 - 2½ minutes at 165°C (330°F)



PIGMENT LOADING Up to 6% MagnaPrint® Eco Pigments



Eco Pigments

**ADDITIVES** 



Retardant Gel Conc, Crosslinker 100, Softener TS Conc



In cool place properly closed: >5°C (40F) <25°C (77F)



**HEALTH & SAFETY**MSDS available upon request



CLEAN UP
Wash off screen using water
and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.